



MAKER METAL 200

Description

Highly refined lightweight fluid specially suited for application in operations to polish ferritic and austenitic stainless steels with low carbon content.

Properties

- Low viscosity and suitable flashpoint mean it can be used with no risk of fire.
- High resistance to ageing, rust and corrosion.
- Helps oil removal if required.

Quality levels, approvals and recommendations

- ISO: MHA

Technical specifications

	UNIT	METHOD	VALUE
Appearance	-	Visual	Clear and bright
Colour	-	ASTM D1500	1
Density at 15 °C	g/mL	ASTM D4052	0.860
Viscosity at 40 °C	cSt	ASTM D445	12
Viscosity at 100 °C	cSt	ASTM D445	3
Flash point, open cup	°C	ASTM D92	175
Pour point	°C	ASTM D97	-9
Aniline point	°C	ASTM D611	95
Noack volatility, 1h at 150 °C	-	DIN 51581	2.5
Corrosion Cu, 3hrs 100 °C	-	ASTM D130	1b
TAN	mg KOH/g	ASTM D974	0.05

The above mentioned characteristics are typical values and should not be considered product specifications.